



Alfombras Sahara Ltda.
Domingo Arteaga Nº 509
Macul - Santiago
CHILE
 Tel. 56 (2) 238 36 71
 Fax 56 (2) 238 66 54
 info@pyramid.cl
 www.pyramid.cl

Tweed

Método de Fabricación	Tufting 1/8" Cutpile
Fibra	100% Polipropileno Stainsafe
Base Primaria	Polipropileno tejido
Base Secundaria	Feltbacking Texflor/Ultratex
Procedencia	Bélgica
Peso de la Fibra	800 gr./m ² +/-
Peso Total	1910 gr/m ² +/-
Altura de Pelo	5,5 mm. +/-
Altura Total	8 mm. +/-
Numero de Puntadas	119.700/m ² .
Ancho del Rollo	4,00 mts.
Resistencia a la Luz	5-6
Resistencia al Agua	4-5
Resistencia Estática	0,12 m ² k/w
Aislamiento Acústico	22dB
Clasificación al Fuego	Efl (EN 13501-1)
Uso	Residencial



Quality Certificate
ISO-9001

Balta Broadloom
 Wakkensteenweg 2
 B-8710 Sint-Baafs-Vijve
 Belgium
 Tel. +32(0)56 62 22 11
 Fax +32(0)56 62 23 55
 www.baltagroup.com



TEXFLOR®
 The backing with textile comfort